



## CX80 RC 77

**Anaerobic sealant for pipes from 3/4" to 3" with low strength. Remains liquid until isolated from oxygen in the presence of metal ions.**

### PROPERTIES:

- low strength
- resistant to oil, water, fuel, hydraulic fluids
- shear strength on steel : 11 N/mm<sup>2</sup>
- initial binding: steel – after 25 minutes, stainless steel – 4.5 hours, brass – 15 minutes
- full strength: steel – after 6 hours, stainless steel – after 36 hours, brass – after 1 hour
- temperature resistance from -55°C to +150°C

### APPLICATION:

- protection against leakage of liquids and gases in metal installations



	bottle 50 ml	bottle 250 ml
package		
cardbox (quantity)	10	10
pallet (quantity)	-	-
barcode	124	258



519076401601244



519076401602586