

STEAM/AL



ZASTOSOWANIE:

Wąż gumowy, nietoksyczny, odpowiedni do gorącej wody i mieszanek parowych. Odpowiedni do pary o temperaturze +120°C.

Standardy: DM 21/3/73 i 18/6/79 + FDA

ZAKRES TEMPERATUR: -40°C +120°C

STRUKTURA:

WARSTWA WEWNĘTRZNA: biała, gładka, odporna na wysokie temperatury, odpowiednia do żywności guma EPDM.

WZMOCNIENIE: silne syntetyczne warstwy tekstylne.

WARSTWA ZEWNĘTRZNA: niebieska, odporna na ścieranie, wysokie temperatury i warunki atmosferyczne guma EPDM. Nie brudzący.

POWIERZCHNIA: gładka, wykończona materiałem.

OZNACZENIE NA WĘŻU: wytłoczone „H.T. /STEAM /AL W.P. 10 BAR (150 PSI) +120°C - FDA”

WSPÓŁCZYNNIK BEZPIECZEŃSTWA: 3:1

APPLICATION:

Softwall rubber hose suitable for hot water and steam mix used where an atoxic hose is required. Suitable to scald with steam up to + 120°C.

Standards: DM 21/3/73 and 18/6/79 + FDA

TEMPERATURE RANGE: -40°C +120°C

CONSTRUCTION:

TUBE: white, smooth, heat resistant food quality EPDM rubber.

REINFORCEMENT: high strength synthetic textile plies.

COVER: blue, abrasion, heat and weathering resistant EPDM rubber. Non staining.

SURFACE: smooth fabric finished.

BRANDING: embossed „H.T. /STEAM /AL W.P. 10 BAR (150 PSI) +120°C - FDA”

SAFETY FACTOR: 3:1

Inne średnice i/lub ciśnienia dostępne są na życzenie. Właściwości i dane techniczne mogą być zmieniane bez uprzedzenia.

Other diameters and/or pressures are available on request. The characteristics and technical data could be changed without warning.

Średnica wew. Inside diameter		Średnica zew. Outside diameter		Waga Weight	Ciś. robocze Working pressure		Ciś. rozrywające Burst pressure		Promień gięcia Bending radius	Długość Length	
mm	inch	mm	inch		bar	psi	bar	psi		mm	m
13	1/2"	23	29/32"	0,37	10	150	30	450	130	40	
16	5/8"	26	1.1/32"	0,43	10	150	30	450	160	40	
19	3/4"	30	1.1/16"	0,55	10	150	30	450	190	40	
25	1"	37	1.15/32"	0,75	10	150	30	450	250	40	